



## Technical Datasheet

# ~~ELS-33~~ El-isol

### Description

~~Kema ELS-33~~ El-isol is added with rust hampering/antirust additives, which leaves a thin isolating and protective rubbery film that effectively protects for at least 12 months, depending on the circumstances.

Recommended on all kind of machinery and tools in use or stored.

~~Kema ELS-33~~ El-isol penetrates wires and protects all cordells, and at the same time leaves a wax-like protective film on the surface of the wire. ~~Kema ELS-33~~ El-isol is used to protect both on and inside steel construction and electrical components.

Excellent on dry as well as wet parts, as the product has good water repellent properties.

~~Kema ELS-33~~ El-isol is extremely isolating on plugs and junction boxes.

### Properties

- for protection against moisture on electronic components
- protects tools, machines etc. against moisture and rust
- for longtime rust protection
- leaves a thin isolating and protective rubbery film
- effective up to +130 °C

### Application

Dries within 30-40 minutes depending on the circumstances.  
Leaves a yellow/brown thin isolating and protective rubbery film.  
Can be removed with ~~EA-264 Moto-Clean~~.

**Observe:** At application in close-fitting electric cupboards, make sure the propellant has evaporated completely before closing the cupboard.



**ITW Chemical Products Scandinavia**

Priorsvej 36 • DK-8600 Silkeborg • Tlf.: +45 86 82 64 44 • Fax: +45 86 82 64 64 • e-mail: info@itw-scan.com • www.itw-scan.com

*Important note: All information and technical data are based on tests which to our knowledge are correct and reliable. However, there are no guarantees. It is the responsibility of the user to make sure that the information is useable and complete in connection with the purpose in question.*

Date: 02.11.2005

INFORMATION

# ~~ELS-33~~ EI-isol

## Technical and physical data

Item no.	05395
Packing	spray can
Contents	500 ml
weight	374 g
Propellant	propane/butane
Colour	brown
Base	mineral oil/wax
Consistency	rubbery
Film thickness	12-17 $\mu$ (one covering layer)
Density at 15°C	0.749 g/cm <sup>3</sup>
Full hardening	90 minutes, (depending on the layer thickness)
Saltfog test (35 $\mu$ )	96 hours without rust
Guiding protection time:	
Indoor	24 months
Outdoor covered	18 months
Outdoor uncovered	10 months
Emptying rate	1,01 g/sec.
Temperature range	-40°C to +130°C

## Information

For further technical information and Material Safety Data Sheet for the ITW products, please contact:

**ITW Chemical Products Scandinavia**

**Priorsvej 36**

**8600 Silkeborg**

**Phone: +45 86 82 64 44**

**Fax: +45 86 82 64 64**

**e-mail: [info@itw-scan.com](mailto:info@itw-scan.com)**

**[www.itw-scan.com](http://www.itw-scan.com)**